

PRODOTTI	CARATTERISTICHE CHIMICHE							
	Al ₂ O ₃ %	CaO %	MgO %	CaF ₂ %	SiO ₂ %	Al.Met %	R ₂ O ₃ %	TiO ₂ %
REFINED ALLUMINA	97/98	< 0,5	< 0,5		< 0,5		< 1	
PREFUSE 90	> 90	< 1	< 1		< 0,2		< 8 (V ₂ O ₅)	< 0,2
PREFUSE 800	80/85	< 1	14/15				< 2 (V ₂ O ₅)	
PREFUSE 6040	60/65	30/35	2/3		< 3		< 2	
PREFUSE 600	50/52	6/8	1/2	36/38	0,5/1			
WOLLASTONITE	10/11	44/45	6/7		36/38		0,5/1	0,5/1
OLIVINITE	10/12	1/2	36/40		40/45		3/4	3/5
CALCIO ALLUMINATO 7520	75 (+/- 2)	20 (+/- 2)	2 (+/- 1)		< 1		2/3	< 0,5
PRODOTTI IN NOCELLE								
CALCIO ALLUMINATO 5030	75 (+/- 2)	30 (+/- 2)	7 (+/- 1)		< 1		< 3	< 1
CALCIO ALLUMINATO 5525	55 (+/- 2)	27 (+/- 2)	7 (+/- 1)		< 1	< 1	< 1	< 1
CALCIO ALLUMINATO 5530	55 (+/- 2)	30 (+/- 2)	12 (+/- 2)		< 1	< 1	< 1	< 1